


Product Dimensions and Weights

DIN 7983C ISO 7051 Specifications

Metric DIN 7983C Cross recessed (Phillips) Raised Countersunk (Oval) Head Tapping Screws



	Thread s	ize	ST2.2	ST2.9	ST3.5	(ST3.9)	ST4.2	ST4.8	ST5.5	ST6.3
	Р		0.8	1.1	1.3	1.3	1.4	1.6	1.8	1.8
	a max.		0.8	1.1	1.3	1.3	1.4	1.6	1.8	1.8
nominal=max		4.3	5.5	6.8	7.5	8.1	9.5	10.8	12.4	
	a DK F K r rf Cross recess	min.	4	5.2	6.44	7.14	7.74	9.14	10.37	11.97
	F	approx.	0.7	0.9	1.2	1.3	1.4	1.5	1.7	2
	K	approx.	1.3	1.7	2.1	2.3	2.5	3	3.4	3.8
	r	max.	0.8	1.1	1.4	1.5	1.6	1.9	2.1	2.4
	rf approx.		3.8	4.6	5.4	6	6.6	8.2	9.4	11.1
Cros	ss recess	No.	1	1	2	2	2	2	3	3
	М	approx.	2.8	3.4	4.6	4.7	4.9	5.4	7	7.4
Type H	Penetration	min.	1.17	1.81	1.89	2.04	2.24	2.7	3.02	3.46
	depth	max.	1.57	2.21	2.39	2.54	2.74	3.2	3.53	3.96
	М	approx.	2.4	3.1	4.3	4.4	4.6	5.1	6.6	7.1
Type Z	Penetration	min.	1.1	1.83	1.88	2	2.26	2.69	2.92	3.4
	depth	max.	1.35	2.08	2.34	2.46	2.72	3.15	3.38	3.86
Υ	max.	Type C	2	2.6	3.2	3.5	3.7	4.3	5	6
	IIIax.	Type F	1.6	2.1	2.5	2.7	2.8	3.2	3.6	3.6

All measurements are in mm

Aspen Fasteners 4807 Rockside Road, Suite 400, Independence, OH 44131 USA www.aspenfasteners.com | aspensales@aspenfasteners.com | 1-800-479-0056



Metric DIN 7983C is a cross recessed (Phillips) raised countersunk (oval) head tapping screws. These screws are designed to cut threads into pre-drilled untapped holes of the substrate into which they are screwed. The recommended pilot hole sizes vary. depending on the diameter of the screw to be used and thickness of the substrate material. These screws are available in zinc plated steel as well as stainless steel A2 and A4. Metric DIN 7983C cross recessed (Phillips) raised countersunk (oval) head tapping screws are fully threaded with a coarse thread and a gimlet point. Recommended to be used in thin gauge sheet metal. resinous plywood. and composite materials. Flat countersunk heads have a flat top surface and a cone-shaped bearing surface with a head angle of approximately 90°. They are used for applications where the head must be flush with the mating surface of the substrate. Aspen Fasteners offers over 500.000 unique fastener products from stock in inch and metric standard in a variety of materials and finishes. The following sizes metric DIN 7983C cross recessed (Phillips) raised countersunk (oval) head tapping screws are available for immediate shipping from stock: Diameters ranging from M2.2 to M6.3 up to 38mm long in zinc plated steel and stainless steel A2 and A4. View parts by clicking on the following link: DIN 7983C cross recessed (Phillips) raised countersunk (oval) head tapping screws

L	Тур	e C	Тур	e F		Weight kg/1000pcs						
nominal	min.	max.	min.	max.								
6.5	5.7	7.3	5.7	6.5	0.18	0.332						
9.5	8.7	10.3	8.7	9.5	0.24	0.44	0.721	0.888	1.07	1.53		
13	12.2	13.8	12.2	13	0.31	0.566	0.898	1.11	1.32	1.88	2.74	3.46
16	15.2	16.8	15.2	16	0.37	0.674	1.05	1.3	1.53	2.18	3.12	4
19	18.2	19.8	18.2	19		0.782	1.2	1.49	1.74	2.48	3.51	4.54
22	21.2	22.8	20.7	22			1.35	1.68	1.95	2.78	3.89	5.08
25	24.2	25.8	23.7	25			1.51	1.87	2.16	3.08	4.28	5.62
32	30.7	33.3	30.7	32					2.65	3.78	5.19	6.88
38	36.7	39.3	36.7	38							5.97	7.96
38	36.7	39.3	36.7	38						4.52	6.45	8.82

DIN (**D**eutsches Institut für **N**ormung - German Institute for Standardization) standards are issued for a variety of components including industrial fasteners as metric DIN 7983C cross recessed (Phillips) raised countersunk (oval) head tapping screws. The DIN standards remain common in Germany. Europe and globally even though the transition to ISO standards is taking place. DIN standards continue to be used for parts which do not have ISO equivalents or for which there is no need for standardization. The ISO equivalent of a metric DIN 7983C cross recessed (Phillips) raised countersunk (oval) head tapping screws is ISO 7051.



1) Mechanical properties of stainless steel for metric DIN 7983C cross recessed (Phillips) raised countersunk (oval) head tapping screws

Stainless steels can be divided into three groups of steel - austenitic. ferritic and martensitic. Austenitic steel is by far the most common type (>90% of commercial fasteners). The steel groups and strength classes are designated by a four-digit sequence of letters and numbers (eg A2-70) as shown in the following table. DIN EN ISO 3506 governs screws and nuts made from stainless steel.

				ts		
Steel group	Steel grade	Strength class	Tensile strength N/mm ²	Tensile strength PSI	Dia range	Nut Load N/mm ²
		50	500	70.000	<=M39	500
Austenitic	A2 and A4	70	700	100.000	<=M20	700
		80	800	118.000	<=M20	800

The tensile stress is calculated with reference to the tensile stress area (see DIN EN ISO 3506-1979). Nuts to be paired with same grade of stainless steel screws

Steel group	Property Strength class	Made From	Characteristics
	50	A1. A2	Soft; cold worked. turned and soft pressed fasteners
Austenitic	70	A2. A4	Cold worked. normal strength formed fasteners
	80	A2. A4	Extreme cold worked. high strength. special applications



2) Chemical composition of stainless steel metric DIN 7983C cross recessed (Phillips) raised countersunk (oval) head tapping screws

Grade	USA Grade	Material designation	Material no.	C %	Si ≤ %	Mn ≤ %	Cr %	Mo %	Ni %
	X 5Cr Ni 1810	1.4301	≤ 0.07	1.0	2.0	17.5 to 19.5	1	8.0 to 10.5	
A 2	A 2 304	X 2 Cr Ni 1811	1.4306	≤ 0.03	1.0	2.0	18.0 to 20.0	ı	10 to 12.0
		X 8 Cr Ni 19/10	1.4303	≤ 0.07	1.0	2.0	17.0 to 19.0	-	11.0 to 13.0
A 4		X 5 Cr Ni Mo 1712	1.4401	≤ 0.07	1.0	2.0	16.5 to 18.5	to	10.0 to 13.0
7	316	X 2 Cr Ni Mo 1712	1.4404	≤ 0.03	1.0	2.0	16.5 to 18.5	2.0 to 2.5 2.0 to	10 to 13

Chemical composition of steel metric DIN 7983C cross recessed (Phillips) raised countersunk (oval) head tapping screws

		CHEM	ICAL COMP	TEMPERING		
PROPERTY CLASS	MATERIAL AND TREATMENT	(0	Р	S	TEMPERING TEMP °C MIN.
		min.	max.	max.	max.	
4.6. 4.8. 5.8. 6.8	Low or medium carbon steel	-	0.55	0.05	0.06	-
8.8	Medium carbon steel quenched. tempered	0.25	0.55	0.04	0.05	425
9.8	Medium carbon steel quenched. tempered	0.25	0.55	0.04	0.05	425
10.9	Medium carbon steel additives e.g. boron. Mn. Cr or Alloy steel - quenched. tempered	0.20	0.55	0.04	0.05	425
12.9	Alloy steel - quenched. tempered	0.20	0.50	0.035	0.035	380



4) Mechanical properties of steel for metric DIN 7983C cross recessed (Phillips) raised countersunk (oval) head tapping screws

	OPERTY CLASS										
MECHANICAL PROPERTY							8.8				
			4.8	5.6	5.8	6.8	Up to M 16	Over M 16	9.8	10.9	12.9
Tensile Strength	nom.		400	500 600		800		900	1000	1200	
(Rm. N/mm²)	m	min.		500	520	600	800	830	900	1040	1220
Vickers Hardness	min.		130	155	160	190	250	255	290	320	385
Vickers naturiess	max		250				320	336	360	380	435
Drinell Llendress	min.		124	147	152	181	319	242	266	295	353
Brinell Hardness	max.		238			385	319	342	363	412	
	min.	HR	71	79	82	89			-	,	
Rockwell Hardness		HRC	-	-	-	-	20	23	28	32	39
RockwellHalulless		HR	95			99			-		
	max.	HRC	-	-	-	-	32	34	37	39	44
Yield Stress ReL.	nom.		320 300 400 480		-						
N/mm²	min.		340	300	420	480	-				
Stress at permanent	no	om.	-			6	40	720	900	1080	
set limit N/mm²	m	nin.	-				640	660	720	940	1100

Disclaimer

Dimensional data and technical information for metric DIN 7983C cross recessed (Phillips) raised countersunk (oval) head tapping screws was obtained from publicly available sources and not acquired through standards agencies. It has been completed and compiled for reference purposes only; where discrepancies are found they are subject to change without notice. Aspen Fasteners makes no warranties or representations regarding the accuracy and validity of the compiled information and data. Contact the relevant standards authorities for accurate and detailed information.